

Technical data sheet

Fentrim[®] grommet black



Updated on:	September 12, 2023
Distributor:	SIGA Cover, Inc
Instructions:	See manual
Packaging unit:	$\varnothing \frac{5}{16}'' - \frac{1}{2}'' \mid \frac{5}{8}'' - \frac{7}{8}'' \mid \frac{7}{8}'' - 1''$ 10 gaskets / box $\varnothing 2'' - 2 \frac{7}{8}'' \mid 2 \frac{3}{4}'' - 3 \frac{1}{2}'' \mid 4'' - 4 \frac{1}{2}'' \mid 6'' - 6 \frac{3}{4}''$ 4 gaskets / box
Composition:	Flexible EPDM grommet with special film/fleece collar (that can be plastered over), with SIGA acrylic pressure sensitive adhesive

Characteristics:

Property		Standards	Units	Values
Dimensions	length x with (product size: x)		Inch mm	6" x 6" 150 mm x 150 mm ($\varnothing x < 1''$) 8" x 8" 230 mm x 230 mm ($\varnothing 2'' < x > 2 \frac{7}{8}''$) 12.6" x 12.6" 320 mm x 320 mm ($\varnothing 2 \frac{7}{8}'' < x > 4''$) 13 $\frac{3}{4}''$ x 13 $\frac{3}{4}''$ 350 mm x 350 mm ($\varnothing x > 6''$)
Temperature resistance			°F °C	-40 °F to +212 °F -40 °C to +100 °C
Processing temperature			°F °C	from +14 °F from -10 °C
Atmospheric exposure		IECC zones 3- 8	months	max. 4
		IECC zones 1- 2	months	max. 3
Air Permeance		ASTM E2178		Pass
Water vapor transmission		ASTM E96 Method A (dry cup method)	US Perms	1.72
Ageing resistance	high permanent adhesive strength and flexibility, can reliably and durably absorb structural movements			
Emissions	Free of halogens and domestic toxins			
Suitability for storage	unlimited store in a cool, dry place in its original box			
Colour	black			